



**HAL**  
open science

# Experimental Characterization of an Earth Eco-Efficient Plastering Mortar

Paulina Faria, Tania Santos, Jean-Emmanuel Aubert

► **To cite this version:**

Paulina Faria, Tania Santos, Jean-Emmanuel Aubert. Experimental Characterization of an Earth Eco-Efficient Plastering Mortar. *Journal of Materials in Civil Engineering*, 2016, 28 (1), pp.04015085. 10.1061/(ASCE)MT.1943-5533.0001363 . hal-01849699

**HAL Id: hal-01849699**

**<https://hal.insa-toulouse.fr/hal-01849699>**

Submitted on 13 Jun 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# 1 **Experimental characterization of an earth eco-efficient plastering mortar**

2 Paulina Faria <sup>1\*</sup>

3 Tânia Santos <sup>2</sup>

4 Jean-Emmanuel Aubert <sup>3</sup>

5

## 6 **ABSTRACT**

7 Earthen plastering mortars are becoming recognized as highly eco-efficient. The  
8 assessment of their technical properties needs to be standardized but only the German  
9 standard DIN 18947 exists for the moment. An extended experimental campaign was  
10 developed in order to assess multiple properties of a ready-mixed earth plastering  
11 mortar and also to increase scientific knowledge of the influence of test procedures on  
12 those properties. The experimental campaign showed that some aspects related to the  
13 equipment, type of samples and sample preparation can be very important, while  
14 others seemed to have less influence on the results and the classification of mortars. It  
15 also showed that some complementary tests can easily be performed and considered  
16 together with the standardized ones, while others may need to be improved. The  
17 plaster satisfied the requirements of the existing German standard but, most  
18 importantly, it seemed adequate for application as rehabilitation plaster on historic and  
19 modern masonry buildings. Apart from their aesthetic aspect, the contribution of  
20 earthen plasters to eco-efficiency and particularly to hygrometric indoor comfort should  
21 be highlighted.

22

## 23 **Subject headings from the ASCE's Civil Engineering Database**

24 Mortar; Prefabrication; Test procedure; Standardization; Classification

---

<sup>1</sup> PhD, CERIS, ICIST, Nova University of Lisbon, Department of Civil Engineering, Caparica Campus, 2829-516 Caparica, Portugal, [paulina.faria@fct.unl.pt](mailto:paulina.faria@fct.unl.pt)

\* corresponding author

<sup>2</sup> MSc, Nova University of Lisbon, Department of Civil Engineering, Caparica Campus, 2829-516 Caparica, Portugal, [tr.santos@campus.fct.unl.pt](mailto:tr.santos@campus.fct.unl.pt)

<sup>3</sup> PhD, Université de Toulouse, UPS, INSA, Laboratoire Matériaux et Durabilité des Constructions, 135, avenue de Ranguel, 31077 Toulouse cedex 4, France, [jean-emmanuel.aubert@univ-tlse3.fr](mailto:jean-emmanuel.aubert@univ-tlse3.fr)

## 25 **Introduction**

26 Mortars are building products that are widely used in construction, principally being  
27 applied as rendering and plastering systems to protect the walls. While renders have to  
28 resist the action of rain water, plasters must contribute to the indoor air quality and  
29 comfort. Therefore plastering mortars must fulfill predetermined requirements.

30 After being neglected for decades, earth-based plastering mortars are nowadays  
31 becoming recognized as highly eco-efficient (Maddison et al., 2009; Darling et al.,  
32 2012). When compared to other types of mortars the sustainability of earth mortars is  
33 well known, mainly in terms of embodied energy (Swan et al., 2011). In fact, this type of  
34 mortar does not contain binders that have to be specifically produced and thus involve  
35 stone mining, transport and energy consumption. Melià et al. (2014) compared the  
36 environmental impacts of earthen plasters with those of conventional plasters based on  
37 common binders (like cement or hydraulic lime) using the LCA methodology. Their  
38 research showed that earth plasters outperformed the others with respect to all the  
39 indicators considered: cumulative energy demand, greenhouse gas protocol, ecological  
40 footprint and ReCiPe indicators (Melià et al., 2014). Aesthetic aspects, like color and  
41 texture, were also recognized. However, the technical characteristics and efficiency of  
42 these mortars has not often been scientifically proved; their technical efficiency needs  
43 to be evidenced by testing.

44 Compared to other types of earth-based products, as the case of earth blocks that  
45 have been deeply studied (Danso et al., 2014; Cagnon et al., 2014; Silveira et al.,  
46 2014), and other types of plastering mortars, such as air lime-based products (Veiga et  
47 al., 2010; Faria et al., 2008), earth-based mortars have been characterized in very few  
48 scientific studies (Pkla et al., 2003; Azeredo et al., 2008; Hamard et al., 2013; Delinière  
49 et al., 2014). There are few codes and standards for earth building materials (Swan et  
50 al., 2011). The recent German standard DIN 18947 (DIN, 2013) is the first standard  
51 specifically devoted to earth mortars. It defines some requirements and test methods.  
52 Many test methods are based on parts of the EN 1015 standard, developed for

53 masonry mortars, mainly hydraulic binder-based, while others are specific to the DIN  
54 standard (DIN, 2013). Delinière et al. (2014) have recently applied this standard to  
55 characterize five ready-mixed earth plasters.

56 The experimental study presented in this paper involved a ready-mixed earth plastering  
57 mortar based on natural earth, sand and plant fibers. The dry ready-mixed product was  
58 characterized in the laboratory. The same ready-mixed product was used to produce  
59 two sets of mortars. The first was prepared in the field with current mechanical  
60 equipment while the second was prepared in controlled laboratory conditions. The  
61 mortar prepared on site was used to plaster an experimental brick masonry wall that  
62 was being non-destructively tested (Faria et al., 2014), and a portion was reserved.  
63 Both mortars were characterized in the fresh state and measurements included drying  
64 shrinkage. Samples with different dimensions and methods of preparation were  
65 produced in the laboratory. The wall plaster and the samples were tested.  
66 Characterization of the hardened mortar included visual observation of the plaster  
67 applied to the brick masonry test wall and several tests performed on mortar samples  
68 to evaluate the mechanical, physical and microstructural properties of the mortar.  
69 Hygrothermal properties of the hardened mortars were also studied (sorption–  
70 desorption isotherms, vapor diffusion and thermal conductivity). The characterization  
71 and the test procedures were based on the German standard (DIN, 2013) but also  
72 included other standards and specific test procedures implemented by the authors.  
73 The influence of differences in the dimensions of samples and the methods for  
74 preparing them were assessed. The characteristics of the plaster are presented and,  
75 whenever possible, compared with the DIN (DIN, 2013) requirements and with other  
76 studies (Delinière et al., 2014; Gomes et al., 2012; Veiga et al., 2010). The aim is to  
77 contribute to the setting up of test procedures, including the validation of existing ones  
78 and the development of complementary procedures to characterize earth plasters.  
79 These indicative results should be useful for a future international standard for earthen  
80 plastering mortars.

81

## 82 **Materials and methods**

### 83 **Materials**

84 The experimental study presented in this paper was carried out with a ready-mixed  
85 earth plastering mortar from the Embarro company (Portugal and Spain), based on  
86 natural clayish earth and siliceous sand, both from the Algarve region (South Portugal),  
87 and cut oat fibers 1-2 cm long. The ready-mixed mortar was mechanically produced on  
88 site using a Putzmeister MP25 mixing and pumping equipment. The same equipment  
89 was used for the application of mortar as a plaster on an experimental hollow brick  
90 masonry wall having a surface area of 2.2 m x 1.8 m with rain protected exposure to  
91 the outdoor environment (Fig. 1). A portion of this mortar was transported to the  
92 laboratory (30 m distance – 2 minutes), where it was tested in fresh state conditions  
93 and samples were prepared: prismatic samples 40 mm x 40 mm x 160 mm were  
94 prepared in metallic molds and a 15 mm-thick mortar layer was applied to the surface  
95 of ceramic hollow brick of surface area of 29.5 cm x 19.5 cm (Fig. 1). The same ready-  
96 mixed mortar product was mixed in the laboratory for 5 minutes with a mixer blade  
97 (commonly used on site), using the same water content as for the on-site mortar. It,  
98 too, was tested in fresh state conditions and samples were prepared: disk samples 90  
99 mm in diameter and either 15 mm or 20 mm thick were prepared in PVC molds over a  
100 polyethylene base and rectangular samples with 200 mm x 500 mm surface and 15  
101 mm thick were prepared in metallic molds (Fig. 1). All the samples were manually  
102 compacted and leveled. The prismatic samples were de-molded when hardened and  
103 all the samples were allowed to reach equilibrium in controlled environmental  
104 conditions at  $20\pm 3^{\circ}\text{C}$  and  $65\pm 5\%$  relative humidity (RH).

105

### 106 **Methods**

107 *Characterization of ready-mixed product and fresh state mortar*

108 The dry ready-mixed mortar product was observed visually and characterized in terms  
109 of loose bulk density, based on EN 1097-3 (CEN, 1998c), dry particle size distribution,  
110 based on EN 1015-1 (CEN, 1998/2006) and by X-ray diffraction test (XRD). XRD was  
111 carried out with a Phillips diffractometer with Co K $\alpha$  radiation, speed of 0.05 °/s and 2 $\theta$   
112 ranging from 3 to 74. Two types of fractions were analysed: a fraction designated as  
113 fine fraction, which has a higher binder concentration and was obtained from the fines  
114 of the ready-mixed product passing a 106  $\mu$ m sieve and a fraction designated as  
115 global, obtained by grinding the ready-mixed product as collected, to pass in the 106  
116  $\mu$ m sieve.

117 The two batches of mortar were tested by: flow table consistency, based on standard  
118 EN 1015-3 (CEN, 1999/2004/2006); bulk density, following standard EN 1015-6 (CEN,  
119 1999/2006a); air content, according to standard EN 1015-7 (CEN, 1998b); and water  
120 content, determined by weight loss after oven drying.

121 The laboratory mortar was also tested for water retention based on draft standard prEN  
122 1015-8 (CEN, 1999). To determine water retention, the weight increase of filter papers  
123 in contact with the fresh mortar specimen for 5 minutes was considered, in relation to  
124 the mortar solid and liquid compositions. Consistency was assessed also by  
125 penetrometer, based on standard EN 1015-4 (CEN, 1998a), and by the slump  
126 occurring in the flow table test sample. For the latter test, the slump of the mortar  
127 specimen was determined by the difference between the height of the mold and that of  
128 the highest point of the slumped test specimen.

129

### 130 *Drying shrinkage*

131 For the mortar mixed on site, linear drying shrinkage was determined on the basis of  
132 standard DIN 18947 (DIN, 2013) by the linear geometrical length reduction due to  
133 drying of six mortar samples 40 mm x 40 mm x 160 mm, assessed when they were de-  
134 molded. For the laboratory mortar, shrinkage was determined by the geometrical

135 reduction of the surface of three 200 mm x 500 mm mortar samples 15 mm thick when  
136 hardened on metallic molds, compared with the dimensions of the molds.

137

#### 138 *Surface cohesion and dry abrasion resistance*

139 The superficial cohesion and dry abrasion resistance were determined to assess the  
140 surface resistance and the eventual necessity for surface hardening (Röhlen and  
141 Ziegert, 2011). Superficial cohesion was determined by the weight increase of an  
142 adhesive tape 70 mm x 50 mm, after it had been pressed with constant intensity on the  
143 surface of the samples of mortar layer on ceramic brick, using the method of Drdácý  
144 et al. (2014), which expresses the loss of particles from the surface of the mortar. The  
145 average and standard deviation of results obtained with six adhesive tapes applied in  
146 two bricks was used.

147 Dry abrasion resistance was determined according to DIN 18947 (DIN, 2013), by the  
148 weight loss of mortar samples after 20 rotations of three different circular polyethylene  
149 brushes 65 mm in diameter, applied to the sample surface with a pressure of 2 kg.  
150 Samples with mortar on hollow brick and samples of 90 mm diameter and 20 mm  
151 thickness were tested.

152

#### 153 *Mechanical characterization*

154 The mechanical characteristics were evaluated using the six prismatic, 40 mm x 40 mm  
155 x 160 mm samples. The dynamic modulus of elasticity was determined based on  
156 standard EN 14146 (CEN, 2004), defined for natural stone, using a Zeus Resonance  
157 Meter. The flexural and compressive strengths were determined according to  
158 standards DIN 18947 (DIN, 2013) and EN 1015-11 (CEN, 1999/2006c) using a Zwick  
159 Rowell Z050 machine, with load cells of 2 kN, for bending loads and 50 kN for  
160 compression.

161 The adhesive strength was determined with the pull-off adhesion test equipment  
162 PosiTest AT-M and pull-head plates 50 mm in diameter, based on standards DIN  
163 18947 (DIN, 2013) and EN 1015-12 (CEN, 2000).

164

165 *Sorption–desorption isotherms and vapor diffusion*

166 Water vapor permeability of the mortar was determined according to DIN 18947 (DIN,  
167 2013), EN 1015-19 (CEN, 1998/2004), EN ISO 12572 (CEN, 2001) and EN 15803  
168 (CEN, 2009b) using the 90-mm-diameter, 20-mm-thick laboratory mortar samples. The  
169 wet method was used and the mortar specimen systems were placed in a climatic  
170 chamber at 23°C and 40% RH.

171 The sorption of the mortar was determined with the 15 mm x 200 mm x 500 mm  
172 rectangular samples in metallic molds initially in equilibrium at 50% RH, according to  
173 DIN 18947 (DIN, 2013). A climatic chamber was programmed for 80% RH and the  
174 water vapor gain after determined periods of time in the climatic chamber (from 0.5 h  
175 up to 12 h) was assessed using a scale of 0.1 g precision. It was also determined by  
176 the same method but using a scale of 0.001 g precision with the 90-mm-diameter  
177 circular samples with thicknesses of 15 mm and 20 mm. The samples were water-  
178 vapor proofed with a polyethylene film on all surfaces except the top one. Both types of  
179 samples were made with the laboratory mortar. The desorption of the mortars, initially  
180 at equilibrium at 80% RH, was also determined. The climatic chamber was  
181 programmed for 50% RH and the weight decrease of the same samples after the same  
182 defined periods of time (from 0.5 h up to 12 h) were determined.

183

184 *Capillary absorption and drying*

185 The analysis of capillary rise is not a general requirement for non-stabilized earth  
186 mortars because they are intended to be applied for plastering the internal surfaces of  
187 walls or as renders but in areas protected from rain. Nevertheless, if the wall where the  
188 mortar is applied presents problems of capillary rise from the ground, the mortar may



189 need to resist capillary absorption. Therefore the capillary absorption of the mortar was  
190 assessed, using EN 15801 (CEN, 2009a) and EN 1015-18 (CEN, 2002), by sequential  
191 weighing of the samples in contact with water to a height of 5 mm. Cubes 40 mm x 40  
192 mm x 40 mm were cut from the prismatic samples, prepared and tested. Three different  
193 types of sample preparation were used: waterproofing the lateral faces of the cubic  
194 samples with an epoxy resin (resin), waterproofing the lateral faces with a polyethylene  
195 film (polyeth.), and without any material to waterproof the lateral faces (simple). A thin  
196 cotton cloth was placed on the bottom face of each sample, to avoid loss of fines, and  
197 was maintained by a thin elastic band. Each sample was placed inside a net basket  
198 and handled in the basket throughout the test (Fig. 2).

199 The capillary curve, with water capillary absorption by contact area with water in  
200 ordinate (in  $\text{kg/m}^2$ ) and the square root of time in abscissa (in  $\text{min}^{0.5}$ ), was plotted. The  
201 capillary coefficient, CC, which represents the initial capillary absorption, was  
202 determined by the slope of the most representative initial segment of the capillary  
203 curve.

204 The drying capacity of the mortar was assessed after samples had been wetted by the  
205 capillary test, as described by EN 16322 (CEN, 2014), but without complete saturation  
206 of the samples and in slightly different environmental conditions. The same samples,  
207 with the three types of lateral surface treatment mentioned above, were used. The  
208 drying curve was plotted with time in abscissa and water content in ordinate (weight /  
209 drying surface, in  $\text{kg/m}^2$ ) and was used to calculate the drying rate (DR) and the drying  
210 index (DI). The DR represented the initial drying of the mortar and was determined by  
211 the slope of the initial portion of the drying curve for each type of sample preparation. A  
212 higher slope of the curve with respect to the horizontal axis reflected a high drying rate  
213 and faster initial drying. The DI represented the difficulty of achieving complete drying,  
214 in equilibrium with the environment, and was calculated following the simplified  
215 procedure presented by Grilo et al. (2014). It was determined for a period of 137 h.

216 All the tests were carried out in a conditioned room at  $20\pm 3^\circ\text{C}$  and  $65\pm 5\%$  RH.

217

218 *Thermal conductivity and microstructure*

219 Thermal conductivity was determined using six prismatic samples and the samples with  
220 a 15-mm mortar layer on hollow brick, from the mortar mixed on site, and also using  
221 the 15 mm and 20 mm thick circular samples with and the 15 mm x 200 mm x 500 mm  
222 in metallic molds rectangular samples of the laboratory mixed mortar. Tests were  
223 performed after drying of the samples and at equilibrium with the laboratory conditions  
224 (20°C, 65% RH). An Isomet 2104 Heat Transfer Analyzer was used with a 60-mm-  
225 diameter contact probe, API 210412. The equipment requires a minimum surface of 60  
226 mm in diameter and a height of 15 mm. The prismatic sample type did not satisfy the  
227 recommendations for using the test equipment as the surface area of the contact probe  
228 exceeded the surface area of the sample.

229 The bulk density was geometrically determined according to DIN 18947 (DIN, 2013)  
230 and EN 1015-10/A1 (CEN, 1999/2006b) on the same prismatic samples, by means of a  
231 digital caliper and a 0.001 g precision digital scale.

232 The open porosity was determined by mercury intrusion porosimetry (MIP) and the  
233 same technique was used for the determination of pore size distribution. MIP was  
234 applied to specimen taken from among the prismatic samples, without the influence of  
235 the substrate, but also to specimen of the mortar layer on hollow brick produced in  
236 controlled laboratory conditions and samples of the plastering mortar applied on the  
237 experimental hollow brick masonry wall, conditioned in the exterior environment  
238 protected from rain. It was determined with a Micromeritics Autopore II mercury  
239 porosimeter. The masses of the test specimens were stabilized at 40°C and the mortar  
240 specimens were prepared so as to occupy the greater part of the 5 cm<sup>3</sup> bulb of the  
241 penetrometer volume. Testing began at low pressures ranging from 0.01 MPa to 0.21  
242 MPa, followed by high pressure analysis from 0.28 MPa to 206.84 MPa, following a test  
243 procedure that is commonly used for lime mortar testing (Grilo et al., 2014).

244

## 245 **Results and discussion**

246 Ready-mixed product and fresh state mortar characterization

247 The average value of loose bulk density and its standard deviation was  $1.17 \pm 0.01$   
248  $\text{kg/dm}^3$ . The ready-mixed product had a reddish color and the dry particle size  
249 distribution (average of three samples) is presented in Fig. 3.

250 The results obtained by XRD are shown in Fig. 4. The main minerals detected on  
251 ready-mixed product were quartz ( $\text{SiO}_2$ ), K-Feldspar ( $\text{KAlSi}_3\text{O}_8$ ), dolomite  
252 ( $\text{CaMg}(\text{CO}_3)_2$ ), illite ( $(\text{K,H}_3\text{O})\text{Al}_2\text{Si}_3\text{AlO}_{10}(\text{OH})_2$ ) and kaolinite ( $\text{Al}_2(\text{Si}_2\text{O}_5)(\text{OH})_4$ ). Other  
253 minerals were detected in low proportions, like calcite ( $\text{CaCO}_3$ ) and hematite ( $\text{Fe}_2\text{O}_3$ ).

254 The fine fraction presented an increase of the proportions of clay minerals (illite and  
255 kaolinite), which is accompanied by k-feldspar, dolomite, calcite and hematite minerals.

256 The mortar (two batches, produced on site and in the laboratory) showed very good  
257 workability when handled. The plaster applied to the brick masonry wall (Faria et al.,  
258 2014) gave a reddish colored surface without shrinkage cracks. Some dispersed plant  
259 fibers could be seen. The average values (and, whenever at least three samples were  
260 tested, the standard deviation) of fresh mortar properties are presented in Table 1.

261 From Table 1, it can be observed that the fresh state characteristics of the mortars  
262 mixed on site and in the laboratory were quite similar, namely in terms of flow table  
263 consistency, bulk density and water content, despite the different equipment and  
264 conditions used for the mortar production. It is probable that the slightly higher air  
265 content and lower bulk density of the mortar mixed on site were due to the mechanical  
266 equipment that produced (and projected) the mortar.

267 Another fact that could have influenced the fresh state characterization was the time  
268 that elapsed between the contact of the clayish mortar product with water and the  
269 moment the tests were performed. In fact the mortar mixed on site was prepared and  
270 applied as plaster on several walls before being transported to the laboratory and  
271 tested. However, tests performed on samples from both the site and the laboratory

272 batches did not reveal differences that could be directly attributed to that situation. This  
273 is very positive because it indicates good stability of the product when fresh.

274 Compared with earth mortars characterized by Gomes et al. (2012), the mortars  
275 considered in the present study had higher bulk density. When the consistency, wet  
276 bulk density and water content of the earth mortar tested here were compared with  
277 those tested by Delinière et al. (2014), the results were observed to be in the same  
278 range.

279

#### 280 Drying shrinkage

281 The average and standard deviation of shrinkage measured on samples 40 mm x 40  
282 mm x 160 mm was  $0.21\pm 0.08\%$ . In the case of 200 mm x 500 mm laboratory  
283 rectangular samples 15 mm thick the average and standard deviation length changes  
284 of the shorter and longer sides of the rectangle were  $0.32\pm 0.00\%$  and  $0.58\pm 0.23\%$ . As  
285 these samples were not de-molded, it was harder to measure shrinkage in this case  
286 than for prismatic molds. It seemed that shrinkage was proportional to the measured  
287 dimension and, for that reason, another mold was filled with laboratory mortar but only  
288 one sample was tested, using a film-faced plywood mold 40 mm x 40 mm x 600 mm  
289 generally used for testing earth for building purposes and following the Alcock test  
290 (Gomes et al., 2014). Drying shrinkage was 0.61% and no crack was observed inside  
291 the mold. No cracking due to drying shrinkage was observed on the plaster applied to  
292 the experimental wall. The drying shrinkage was very low regardless of the samples  
293 used, including the plaster applied to the experimental wall. The shrinkage measured  
294 on the prismatic samples, according to DIN 18947 (DIN, 2013), was well beyond the  
295 maximum of 3% defined for mortars with fibers. Comparison with the results obtained  
296 with samples of other dimensions suggests that the shrinkage increases in direct  
297 relation with the length of the sample.

298

#### 299 Surface cohesion and dry abrasion resistance

300 The cohesion test was easily performed and allowed the superficial loss of material to  
301 be assessed quantitatively, by weighing. It was  $0.10 \pm 0.03$  g.

302 It seems that, even if a precision scale is not available, the visual observation of the  
303 material sticking to the adhesive tape can be qualitatively compared (Fig. 5). In real  
304 conditions, this easy test can, therefore, be used for comparison between plasters and  
305 between different areas of the same plaster. Comparing the results obtained by  
306 Drdácký et al. (2014) for lime mortars using the same test methods, it is possible to  
307 conclude that the loss of material obtained with the clayish plaster is higher, showing a  
308 lower surface cohesion.

309 The abrasion relief formed on disk samples with the three brushes can be seen in Fig.  
310 6. The soft brush, when pressed, exceeded the diameter of the disc. As the abrasion  
311 with that brush was almost inexistent, it could not be measured with the mortar on brick  
312 sample because of the scale precision.

313 The average and standard deviation of weight loss by abrasion on circular mortar  
314 samples and on mortar-on-brick samples after testing with hard, medium and soft  
315 brushes are presented in Table 2. The standard DIN 18947 (DIN, 2013) defines two  
316 classes, SI and SII, for mortars considering their weight loss by abrasion and their  
317 lower limits are also given in Table 2.

318 The differences of weight loss by abrasion of the mortar obtained with different brushes  
319 are noteworthy. With the soft brush, the mortar would be classified in class SII, while  
320 with the other two brushes the mortar does not meet the standard requirement.

321 Bearing in mind that DIN 18947 (DIN, 2013) only defines a plastic brush, it seems that  
322 the hardness of the brush should be defined with more precision. The DIN standard  
323 also defines that, instead of measuring the weight loss, the disaggregated material  
324 should be weighed. That procedure would appear to be less accurate because, due to  
325 the abrasion of the brush, some of the material would be scattered and, therefore, it  
326 would be difficult to gather and weigh the totality.

327

328 Mechanical characterization

329 The average and standard deviation of the dynamic modulus of elasticity ( $E_d$ ), flexural  
330 and compressive strength ( $F_{Str}$  and  $C_{Str}$ ), and adhesive strength ( $A_{Str}$ ) of the mortar  
331 are presented, together with the lower limits of DIN 18947 (DIN, 2013) strength classes  
332 SI and SII, in Table 3. The fracture pattern of the adhesion test was an adhesive  
333 rupture at the interface between mortar and brick, effectively representing the adhesive  
334 strength.

335 The results presented in Table 3 show that this mortar can be classified as SI because  
336 its flexural strength is not less than  $0.3 \text{ N/mm}^2$ , its compressive strength is not less than  
337  $1.0 \text{ N/mm}^2$  and its adhesive strength is not less than  $0.05 \text{ N/mm}^2$  (DIN, 2013).  
338 Compared with earth mortars characterized by Gomes et al. (2014), the mortars  
339 analyzed in the present study have higher dynamic modulus of elasticity, flexural  
340 strength and compressive strength. Compared with five earth mortars characterized by  
341 Delinière et al. (2014) the tested mortar presents flexural and compressive strengths  
342 that are lower (though only slightly). Nevertheless the mortar tested has a higher  
343 adhesive strength, which may show the influence that different supports can have on  
344 this test. In fact, not only the support but also its preparation may have a huge  
345 influence on results (Delinière et al., 2014). Different, simple tests may be considered  
346 to assess adhesion, such as the one established by Hamard et al. (2013), which can  
347 be easily applied on site to evaluate the compatibility of plasters with the substrate.

348 Veiga et al. (2010) suggest a range of mechanical characteristics of plastering mortars  
349 to ensure compatibility with historic masonry: dynamic modulus of elasticity 2000-5000  
350  $\text{N/mm}^2$ , flexural strength 0.2-0.7  $\text{N/mm}^2$  and compressive strength 0.4-2.5  $\text{N/mm}^2$ .  
351 Although the range was defined for lime-based mortars, it seems acceptable that the  
352 same range should be also considered for plastering mortars to be applied to other  
353 masonries with similar mechanical characteristics. It can be noted that the mechanical  
354 characteristics of the ready-mixed earth mortar are all within the suggested range.

355

356 Sorption–desorption isotherms and vapor diffusion

357 The water vapor resistance factor,  $\mu$ , was  $8.0\pm 0.3$  and the water vapor diffusion  
358 equivalent air layer thickness,  $S_d$ , was  $0.16\pm 0.01$  m (average and standard deviation).

359 The DIN 18947 (DIN, 2013) states that a value of 5 - 10 can generally be adopted for  
360 the water vapor resistance factor of earth mortars (dry and wet method, respectively).

361 The mortar analyzed confirmed that assumption.

362 Cagnon et al. (2014) obtained values of  $\mu$  between 3 and 6 with different types of  
363 earthen bricks, in a chamber at 50% RH and 20°C. Although bricks and plasters were  
364 applied and tested with different thickness, a comparison of the results stressed the  
365 remarkable water vapor permeability of the ready-mixed plaster.

366 The water vapor weight gain and release are presented in Fig. 7. When comparing the  
367 adsorption of the mortar by the standardized rectangular sample with  $1000\text{ cm}^2$  surface  
368 area with the lower limits of classes defined by DIN 18947 (DIN, 2013) (WSI, WSII and  
369 WSIII) it can be seen that the mortar can be classified in class WSIII. Nevertheless,  
370 and despite the apparently different results obtained with the other samples, for a much  
371 smaller surface of  $28.3\text{ cm}^2$ , the same class would be obtained for both types of  
372 samples with 90 mm diameter and 15 mm or 20 mm thickness. Although the  
373 rectangular samples show an initial increase on adsorption, their following behavior is  
374 parallel to that of the circular samples. There is no difference in sorption between  
375 circular samples, regardless of their thickness.

376 Concerning desorption, behavior is similar for the circular and rectangular samples,  
377 particularly during the first half of the test.

378

379 Capillary absorption and drying

380 The capillary curves of the mortar tested for each type of sample preparation is  
381 presented in Fig. 8, with the most representative segments of capillary absorption and  
382 their equations. As explained in Methods the slope of those segments represents the  
383 capillary coefficient.

384 The drying curve of the mortar for each type of sample preparation is presented in Fig.  
385 9, with the segments of initial drying for the determination of the drying rate (DR).

386 The average and standard deviation of capillary coefficient, CC, drying rate, DR, and  
387 drying index, DI, of the mortar samples prepared in different ways – waterproofing of  
388 lateral surfaces with resin or polyethylene film and simple (without waterproofing) - are  
389 presented in Table 4.

390 The capillary test showed that the preparation of the samples (without lateral  
391 waterproofing or with polyethylene film or with resin) has an important influence on  
392 results. For that reason, it seems to be very important to define the sample preparation  
393 procedure if capillary requirements are considered. In terms of sample preparation, DR  
394 results show the same tendency as CC; simple samples and resin samples show the  
395 same tendency for DI and CC, while the samples with polyethylene present a different  
396 tendency.

397 The mortars without mineral binder and with resin preparation used by Gomes et al.  
398 (2012) presented a CC of  $0.14 \text{ kg}/(\text{m}^2 \cdot \text{s}^{0.5})$  without fibers and  $0.23 \text{ kg}/(\text{m}^2 \cdot \text{s}^{0.5})$  with  
399 hemp fibers; their DI was 0.11 without fibers and 0.13 with hemp fibers. The period of  
400 time for the determination of DI by Gomes et al. (2012) was not the same as that of the  
401 present study and, also, the samples of the present study were not totally capillary  
402 saturated before starting the drying test (for that reason, DI is not strictly comparable).  
403 Nevertheless, when comparing the mortars characterized by Gomes et al. (2012) with  
404 the ones of the present study, it can be observed that the latter have a much lower  
405 capillary coefficient ( $0.5 \text{ kg}/(\text{m}^2 \cdot \text{min}^{0.5})$  corresponding to  $0.06 \text{ kg}/(\text{m}^2 \cdot \text{s}^{0.5})$ ), meaning that  
406 the rising water progresses more slowly, but a higher drying index of 0.18, meaning  
407 that total drying is achieved later.

408

409 Thermal conductivity and microstructure

410 The thermal conductivity results (average and standard deviation for each type of  
411 sample) are presented in Table 5.



412 Independently of their type, all the samples had a value close to 0.9 W/(m.K), which  
413 seems to be interesting for non-thermal plasters. Considering a 2-cm-thick plaster and  
414 comparing it with a plaster with chemical binder (with thermal conductivity around 1.3  
415 W/(m.K), the thermal resistance increase due to the earth plaster presented here would  
416 be 0.04 (m<sup>2</sup>.K)/W.

417 Bulk density determined geometrically and from open porosity measured by MIP for the  
418 prismatic samples, and MIP determinations for the mortar layer on brick and the plaster  
419 on the outdoor protected experimental wall are given in Table 6.

420 The plastering mortar can be placed in class 1.8 in terms of dry bulk density (DIN,  
421 2013) because the bulk density is between 1.61-1.80 kg/dm<sup>3</sup>. The porosity determined  
422 by MIP is quite similar for the different types of samples of the same mortar.

423 Incremental mercury porosimetry curves for specimens of prismatic mortar, mortar on  
424 brick, and brick masonry plaster – for the whole range and only the lower part of the  
425 range - are plotted in Fig. 10. The pore size diameter is expressed in microns and each  
426 step of the mercury intrusion is in ml/g.

427 It can be observed from the curves of Fig. 10 (a) that both the mortar plaster on brick  
428 masonry and the mortar on laboratory brick samples present almost the same  
429 microstructure in terms of most frequent pore diameter (approximately 40 μm) and  
430 differential mercury intrusion (approximately 0.20 ml/g). This shows that the mortar's  
431 microstructure is not influenced by the environmental conditioning (in outdoor protected  
432 conditions or in laboratory conditions) for the higher range of pores. The mortar  
433 specimen from a prismatic sample presents a quite different microstructure, with most  
434 frequent pore diameters at around 55 μm and 14 μm, with 0.18 ml/g and 0.12 ml/g  
435 respectively. This bi-modal microstructure of the mortar applied without the influence of  
436 a porous support, compared with samples of the same mortar but applied in contact  
437 with ceramic brick, shows that the support has a notable influence on the mortar's  
438 microstructure. In fact the brick support increases the quantity of pores with larger  
439 diameter while decreasing the quantity with smaller diameters.

440 When the lower range of pores (Fig. 10b) is studied, two peaks can be observed:  
441 around 6  $\mu\text{m}$  mainly for the specimen from the prismatic sample and around 0.1  $\mu\text{m}$  for  
442 all samples. This is the range commonly recognized to have the most influence on the  
443 capillary absorption of building materials (Mindess et al., 1981). However, this  
444 statement is based on studies for cement-based materials and not specifically those on  
445 earth mortars. For the latter type of mortars, the influence of the microstructure needs  
446 to be studied in greater depth.

447

## 448 **Conclusions**

449 The workability achieved by both batches of the ready-mixed earth mortar was  
450 excellent. Results of flow table consistency, wet bulk density and drying shrinkage  
451 satisfied the requirements of DIN 18947 (DIN, 2013) for earth plasters even with  
452 different mixing procedures. These tests seem appropriate for fresh state  
453 characterization and demonstrate good stability of the characteristics with different  
454 types of mixing equipment.

455 The mortar presents good mechanical characteristics when compared to air lime  
456 mortars. It seems appropriate for application on historic walls (Veiga et al., 2010). The  
457 resistance to abrasion is an issue that it is important to address for this type of mortars  
458 but it is necessary to increase the detail of the test procedure mentioned in the DIN  
459 18947 (DIN, 2013), namely in terms of the hardness of the brush used and the  
460 assessment of the loss of weight, for comparability.

461 The mortar showed a very high adsorption capacity, and also the ability to desorb all  
462 the water vapor adsorbed. The hygroscopic behavior of the mortar, and of similar  
463 mortars analyzed by other authors, leads to the conclusion that this type of earth  
464 mortars can indeed contribute to the hygrometric equilibrium and comfort inside  
465 buildings.

466 The capillary absorption measurement is not a common requirement for this type of  
467 mortars but it enables the assessment of their behavior to be broadened, which may be

468 important for some applications and uses. The definition of the lateral waterproofing of  
469 the samples is crucial for comparison, as the results are more favorable when the  
470 lateral waterproofing seems more efficient. Drying capacity can also be easily  
471 assessed. The thermal conductivity does not seem as important for common plaster,  
472 where the layers are not thick.

473 The dry bulk density determined geometrically is quite reliable. The microstructure is  
474 also quite stable when the plaster is applied to different substrates (porous or metallic)  
475 and under different environmental conditions (protected exterior or laboratory).

476 The ready-mixed mortar tested fulfilled all the DIN 18947 (DIN, 2013) requirements  
477 assessed and showed an appropriate behavior when applied to a hollow brick test wall  
478 in protected outdoor conditions.

479 It is expected that the results will contribute to a more generalized use of earth mortars  
480 as plasters, or as renders in areas protected from rain, on historic but also on modern  
481 masonries. The implementation of an international standard, where test procedures  
482 and requirements were defined, would also help to achieve this goal.

483

#### 484 **Acknowledgements**

485 The authors wish to acknowledge the EMBARRO company for supporting the earth  
486 plaster workshop where the plaster was produced and are particularly grateful to Vitor  
487 Silva for his help throughout the testing campaign.

488

#### 489 **References**

- 490 Azeredo, G., Morel, J.-C. (2008). "Applicability of rheometers to characterizing earth  
491 mortar behavior. Part I: experimental device and validation." *Materials and Structures*,  
492 41, 1465-1472. Doi: 10.1617/s11527-007-9343-9
- 493 Cagnon, H., Aubert, J.E., Coutand, M., Magniont, C. (2014). "Hygrothermal properties  
494 of earth bricks." *Energy Building*, 8, 208-217. Doi: 10.1016/j.enbuild.2014.05.024

495 Danso, H., Martinson, B., Ali, M. & Mant, C. (2014). "Performance characteristics of  
496 enhanced soil blocks: a quantitative review." *Building Research & Information*. Doi:  
497 10.1080/09613218.2014.933293

498 Darling, E., Cros, C., Wargocki, P., Kolarik, J., Morrosin, G., Corsi, R. (2012). "Impacts  
499 of clay plaster on indoor air quality assessed using chemical and sensory  
500 measurements." *Building and Environment*, 57, 370-376. Doi:  
501 10.1016/j.buildenv.2012.06.004

502 Delinière, R., Aubert, J.E., Rojat, F., Gasc-Barbier, M. (2014). "Physical, mineralogical  
503 and mechanical characterization of ready-mixed clay plaster." *Building and  
504 Environment*, 80, 11-17. Doi: 10.1016/j.buildenv.2014.05.012

505 DIN (2013). "DIN 18947 – Earth plasters – Terms and definitions, requirements, test  
506 methods (in German)", Berlin.

507 Drdácký, M., Lesák, J., Niedoba, K., Valach, J. (2014). "Peeling tests for assessing the  
508 cohesion and consolidation characteristics of mortar and render surfaces." *Materials  
509 and Structures*. Doi: 10.1617/s11527-014-0285-8

510 CEN (1998/2006). *EN 1015-1/A1*. "Methods of test for mortar for masonry. Part 1:  
511 Determination of particle size distribution (by sieve analysis)", Brussels.

512 CEN (1999/2004/2006). *EN 1015-3/A1/A2*. "Methods of test for mortar for masonry.  
513 Part 3: Determination of consistence of fresh mortar (by flow table)", Brussels.

514 CEN (1998a). *EN 1015-4*. "Methods of test for mortar for masonry. Part 4:  
515 Determination of consistence of fresh mortar (by plunger penetration)", Brussels.

516 CEN (1999/2006a). *EN 1015-6/A1*. "Methods of test for mortar for masonry. Part 6:  
517 Determination of bulk density of fresh mortar", Brussels.

518 CEN (1998b). *EN 1015-7*. "Methods of test for mortar for masonry. Part 7:  
519 Determination of air content of fresh mortar", Brussels.

520 CEN (1999). *prEN 1015-8*. "Draft European Standard - Methods of test for mortar for  
521 masonry. Part 8: Determination of water retentivity of fresh mortar", Brussels.

522 CEN (1999/2006b). *EN 1015-10/A1*. "Methods of test for mortar for masonry. Part 10:  
523 Determination of dry bulk density of hardened mortar", Brussels.

524 CEN (1999/2006c). *EN 1015-11/A1*. "Methods of test for mortar for masonry. Part 11:  
525 Determination of flexural and compressive strength of hardened mortar", Brussels.

526 CEN (2000). *EN 1015-12*. "Methods of test for mortar for masonry. Part 12:  
527 Determination of adhesive strength of hardened rendering and plastering mortars on  
528 substrates", Brussels.

529 CEN (2002). *EN 1015-18*. "Methods of test for mortar for masonry. Part 18:  
530 Determination of water absorption coefficient due to capillary action of hardened  
531 mortar", Brussels.

532 CEN (1998/2004). *EN 1015-19/A1*. "Methods of test for mortar for masonry. Part 19:  
533 Determination of water vapour permeability of hardened rendering and plastering  
534 mortars", Brussels.

535 CEN (1998c). *EN 1097-3*. "Tests for mechanical and physical properties of aggregates.  
536 Part 3: Determination of loose bulk density and voids", Brussels.

537 CEN (2001). *EN ISO 12572*. "Hygrothermal performance of building materials and  
538 products. Determination of water vapour transmission properties", Brussels.

539 CEN (2004). *EN 14146*. "Natural stone test methods. Determination of the dynamic  
540 modulus of elasticity (by measuring the fundamental resonance frequency)", Brussels.

541 CEN (2009a). *EN 15801*. "Conservation of cultural property. Test methods.  
542 Determination of water absorption by capillarity", Brussels.

543 CEN (2009b). *EN 15803*. "Conservation of cultural property. Test methods.  
544 Determination of water vapour permeability", Brussels.

545 CEN (2014). *EN 16322*. "Conservation of Cultural Heritage. Test methods.  
546 Determination of drying properties", Brussels.

547 Faria, P., Henriques, F., Rato, V. (2008). "Comparative evaluation of aerial lime  
548 mortars for architectural conservation". *Journal of Cultural Heritage*, 9 (3), 338-346.  
549 Doi: 10.1016/j.culher.2008.03.003

550 Faria, P., Santos, T., Silva, V. (2014). "Earth-based mortars for masonry plastering". In:  
551 9th International Masonry Conference (CD).

552 Gomes, M.I., Gonçalves, T.D., Faria, P. (2012). "Earth-based repair mortars:  
553 experimental analysis with different binders and natural fibers." In: Mileto, Vegas &  
554 Cristini, editors. Rammed Earth Conservation 2012. London: Taylor & Francis, 661-  
555 668.

556 Gomes, M.I., Gonçalves, T.D., Faria, P. (2014). "Unstabilised rammed earth:  
557 characterization of material collected from old constructions in South Portugal and  
558 comparison to normative requirements." *International Journal of Architectural Heritage*,  
559 8, 185-212. Doi: 10.1080/15583058.2012.683133

560 Grilo, J., Faria, P., Veiga, R., Santos-Silva, A., Silva, V., Velosa, A. (2014). "New  
561 natural hydraulic lime mortars. Physical and microstructural properties in different  
562 curing conditions." *Construction Building Materials*, 54, 378-384. Doi:  
563 10.1016/j.conbuildmat.2013.12.078

564 Hamard, E., Morel, J.C., Salgado, F., Marcom, A., Meunier, N. (2013). "A procedure to  
565 assess the suitability of plaster to protect vernacular earthen architecture." *Journal of*  
566 *Cultural Heritage*, 14, 109-115. Doi: 10.1016/j.culher.2012.04.005

567 Maddison, M., Muring, T., Kirsimae, K., Mander, U. (2009). "The humidity buffer  
568 capacity of clay-sand plaster filled with phytomass from treatment wetlands." *Building*  
569 *and Environment*, 44, 1864-1868. Doi: 10.1016/j.buildenv.2008.12.008

570 Melià, P., Ruggieri, G., Sabbadini, S., Dotelli, G. (2014). "Environmental impacts of  
571 natural and conventional building materials: a case study on earth plasters." *Journal of*  
572 *Cleaner Production*, 80, 179-186. Doi: 10.1016/j.buildenv.2012.06.004

573 Mindess, S., Young, J.F., Darwin, D. Concrete. Englewood Cliffs, N. J.: Prentice-Hall  
574 Inc.; 1981.

575 Pkla, A., Mesbah, A., Rigasse, V., Morel, J.-C. (2003). "Empirical comparison of testing  
576 methods on measurements of the mechanical characteristics of soil mortars." *Materials*  
577 *and Structures*, 36, 108-117. Doi: 10.1007/BF02479524

578 Röhlen, E., Ziegert, C. (2011). *Earth building practice*. 1st ed., Beuth Verlag GmbH,  
579 Berlin.

580 Silveira, D., Varum, H., Costa, A., Carvalho, J. (2014). "Mechanical Properties and  
581 Behavior of Traditional Adobe Wall Panels of the Aveiro District." *Journal of Materials in*  
582 *Civil Engineering*. Doi: 10.1061/(ASCE)MT.1943-5533.0001194

583 Swan, A., Rteil, A., Lovegrove, G. (2011). "Sustainable Earthen and Straw Bale  
584 Construction in North American Buildings: Codes and Practice." *Journal of Materials in*  
585 *Civil Engineering*, 23(6), 866–872. Doi: 10.1061/(ASCE)MT.1943-5533.0000241

586 Veiga, R., Fragata, A., Velosa, A.L., Magalhães, A.C., Margalha, G. (2010). "Lime-  
587 based mortars: viability for use as substitution renders in historical buildings."  
588 *International Journal of Architectural Heritage*, 4, 177-195. Doi:  
589 10.1080/15583050902914678

590 **Figure captions**

591 **Fig. 1.** Samples and tests performed.

592 **Fig. 2.** Capillary samples prepared with resin and cotton cloth (left) and with  
593 polyethylene film inside the net basket (right).

594 **Fig. 3.** Dry particle size distribution of the ready-mixed mortar product.

595 **Fig. 4.** X-ray diffraction of global and fine samples of the ready-mixed product (Q -  
596 quartz, F - K-Feldspar, D - dolomite, M – illite, K – kaolinite, C – calcite, H - hematite).

597 **Fig. 5.** Visual result of the cohesion test with material sticking to the adhesive tape.

598 **Fig. 6.** Abrasion relief of the circular mortar samples tested with brushes of different  
599 hardness.

600 **Fig. 7.** Sorption and desorption of mortar samples.

601 **Fig. 8.** Capillary curves of mortar samples with different preparation, representative  
602 segment of capillary absorption, their equation and correlation coefficient.

603 **Fig. 9.** Drying curves of mortar samples with different preparations, segments of initial  
604 drying, their equation and correlation coefficient.

605 **Fig. 10.** Incremental mercury porosimetry curves – whole range (a) and only lower part  
606 of the range (b).

607



608 **Table 1.** Characteristics of fresh mortars.

Fresh Mortar	On site	Laboratory
Flow table consistency [mm]	178.8±2.5	182.3±2.5
Slump by flow table [mm]	-	14.2
Penetrometer consistency [mm]	-	2.4±0.1
Wet bulk density [kg/dm <sup>3</sup> ]	2.03	2.11
Air content [%]	2.8	2.5
Water retention [%]	-	67.5±1.3
Water content [%]	20.1±0.1	19.4±0.3

609

610

611 **Table 2.** Weight loss by abrasion and standard lower limits.

$\Delta Wt$ [g]	Ø9cm, 2cm			Mortar on brick		
	Hard	Medium	Soft	Hard	Medium	Soft
Average	18.1	3.9	0.3	11.2	4.5	-
StDv	3.1	0.5	0.0	2.2	0.5	-
SI (DIN, 2013)				≤1.5		
SII (DIN, 2013)				≤0.7		

612

613

614 **Table 3.** Dynamic modulus of elasticity, flexural, compressive and adhesive strength of  
615 the mortar (average and standard deviation) and standard lower limits.

Dry Mortar	Ed [N/mm <sup>2</sup> ]	FStr [N/mm <sup>2</sup> ]	CStr [N/mm <sup>2</sup> ]	AStr [N/mm <sup>2</sup> ]
Average	3610	0.3	1.1	0.15
Stdv	128	0.0	0.1	0.03
SI (DIN, 2013)	-	≥0.3	≥1.0	≥0.05
SII (DIN, 2013)	-	≥0.7	≥1.5	≥0.1

616

617

618 **Table 4.** Capillary coefficient, CC, drying rate, DR, and drying index, DI, of the mortar  
 619 (average and standard deviation).

Dry mortar	CC [kg/(m <sup>2</sup> .min <sup>0.5</sup> )]			DR [kg/(m <sup>2</sup> .h)]			DI [-]		
	Prepar.	Resin	Polyeth.	Simple	Resin	Polyeth.	Simple	Resin	Polyeth.
Average	0.50	0.86	1.84	0.30	0.33	0.64	0.18	0.22	0.14
Stdv	0.06	0.04	0.34	0.01	0.02	0.07	0.01	0.02	0.03

620

621

622 **Table 5.** Thermal conductivity of mortars for different types of samples (average and  
623 standard deviation).

Sample	$\lambda$ [W/(m.K)]				
	Ø9cm 1.5cm	Ø9cm 2.0cm	Rectangular 1.5cm	1.5 m on Brick	Prismatic
Average	0.8	0.9	0.9	0.9	1.0
Stdv	0.0	0.0	0.0	0.1	0.0

624

625

626 **Table 6.** Open porosity, bulk density and standard class of mortar on a prismatic  
627 sample, a plaster-on-brick sample and from the brick masonry plaster.

Sample		Bulk density [kg/dm <sup>3</sup> ]	Porosity [%]	Class (DIN, 2013)
Prismatic	Geometric	1.77 ±0.02	-	1.8
	MIP	1.78	31	
Plaster (MIP)		1.81	30	2.0
On brick (MIP)		1.99	31	

628